

Typical Properties

	<i>Piccotac 1020</i>	<i>Piccotac 1095</i>	<i>Piccotac 1098</i>	<i>Piccotac 1100</i>	<i>Piccotac 1115</i>
Softening point, R&B, °C	6	95	100	101	112
Color, Gardner	3	2	2	2	2
T _g , °C (midpoint)	—	43	47	46	58
MMAF, °C	92	94	94	96	99
DACP, °C	43	52	57	62	69
OMSCP, °C	<-50	<-40	<-40	<-40	<-40
M _r	3,800	3,500	4,950	8,250	15,900
M _w	1,750	1,700	2,150	2,900	3,800
M _n	800	800	900	950	1,100
M _w /M _n	2.1	2.1	2.4	3.0	3.4