

**Specified Properties:**

<b>Softening Point, °C</b>	89~96
<b>Gardner Color / YI</b>	4.0 Max / 34 Max
<b>Appearance</b>	Transparent light yellow solids

**Typical Properties:**

<b>Softening Point, °C</b>	91.0
<b>Color, Gardner / YI (Initial)</b>	3.3 / 26
<b>Wax Cloud Point, °C</b> (EVA / Resin / Wax)	95 (30 / 45 / 25)
<b>Thermal Color Stability (YI)</b> 5 hours @ 175 °C	55
<b>Glass Transition Temperature (Tg), °C</b>	49
<b>Melt Viscosity (cP), 160 °C</b>	710
<b>Molecular Weight</b>	
<b>Mw</b>	1747
<b>Mn</b>	1072
<b>Insolubles, wt%</b>	0.02